# **NICKEL ALLOY**

# 825 - 2.4858



#### 825 - 2.4858

Nickel Alloy 825 is a nickel-iron-chromium alloy with additions of molybdenum, copper and titanium. Commonly referred to as Incoloy 825, this alloy is recognised for its excellent corrosion resistance in challenging environments, including those with sulfuric and phosphoric acids, and outstanding resistance to pitting and crevice corrosion, as well as to chloride-ion stress corrosion cracking.

#### **KEY FEATURES**

- Excellent corrosion resistance
- High temperature resistance
- Optimal longevity in challenging environments
- General weldability

#### **CHEMICAL PROPERTIES**

| Nickel | Chromium   | Iron | Molybdenum | Copper | Manganese | Titanium | Silicone | Aluminium | Carbon | Sulphur |
|--------|------------|------|------------|--------|-----------|----------|----------|-----------|--------|---------|
| (Ni)   | (Cr)       | (Fe) | (Mo)       | (Cu)   | (Mn)      | (Ti)     | (Si)     | (Al)      | (C)    | (S)     |
| 38-46% | 19.5-23.5% | 22%  | 2.5-3.5%   | 1.5-3% | 1%        | 0.6-1.2% | 0.5%     | 0.2%      | 0.05%  |         |

## **MECHANICAL PROPERTIES**

| Tensile strength (N/mm <sup>2</sup> ) | 590   |
|---------------------------------------|-------|
| Yield strength (N/mm <sup>2</sup> )   | 241   |
| Elongation (% in 4D)                  | 30    |
| Hardness - Rockwell (HRB) max         | 80-85 |
| Hardness - Brinell (HB) max           | 320   |

## PHYSICAL PROPERTIES

| Density (kg/m³)             | 8140                         |      |  |
|-----------------------------|------------------------------|------|--|
| Modulus of elasticity (Gp   | asticity (Gpa)               |      |  |
| Maan as officient of        | 0-100°C (µm/m/°C)            | 14.0 |  |
| Mean coefficient of         | 0-350°C (µm/m/°C)            | 14.9 |  |
| thermal expansion           | 0-538°C (µm/m/°C)            | 15.4 |  |
| Thermal                     | at 100°C (W/m.K)             | 11.1 |  |
| conductivity                | at 500°C (W/m.K)             | 13.5 |  |
| Specific Heat 0-100°C (J    | ,                            | 440  |  |
| Electrical resistivity (nΩ. | lectrical resistivity (nΩ.m) |      |  |
| Melting point (°C)          | 1400                         |      |  |



#### **MARKET SECTORS**








Equipment for sour gas, tubing and piping




Seawater piping systems, heat exchangers, valves, ship fittings











Scrubbers, ductwork, waste incinerators, reactors

West Midlands - Blackburn - Dorset - Bristol -Visit our website: www.ppbornmoremetals.co.uk